



# Polar Kraft® R

## End Uses

A strong, bleached, high performance paper with the stiffness needed for high conversion rates into multiwall bags. Polar Kraft® "R" is recommended for applications demanding high CD strength and superior converting runnability.

## Fibre Source

British Columbia's northern forests produce some of the finest trees and fibre available for paper. The ideal climate encourages slow growth of white spruce, lodgepole pine and alpine fir. These trees produce cellulose fibres that are long, slender, flexible, and strong - providing an excellent furnish for kraft paper production. The readily collapsible thin cell walls of Canfor Pulp's fibres form ribbons with an exceptional surface area - promoting optimum fibre to fibre bonding for superior strength.

Typical Values – Imperial (1924-3)

Basis Weight		lb/3000ft <sup>2</sup>	50	60	Test Method
TEA	MD	ft.lbs/ft <sup>2</sup>	8.0	10.7	ISO 1924-3
	CD	ft.lbs/ft <sup>2</sup>	15.4	18.1	ISO 1924-3
TEA Index	MD	J/g	1.5	1.5	ISO 1924-3
	CD	J/g	2.8	2.8	ISO 1924-3
Tensile	MD	lbs/in.	40.2	45.8	ISO 1924-3
	CD	lbs/in.	22.8	27.6	ISO 1924-3
Stretch	MD	%	2.5	2.9	ISO 1924-3
	CD	%	8.2	8.0	ISO 1924-3
Porosity		s/100mL	26	28	ISO 5636-5
Tear	MD	g	114	143	ISO 1974
	CD	g	119	156	ISO 1974
Moisture		%	7.2	7.2	ISO 287

Paper Laboratory Conditions: 50% RH, 73.4°F

Brightness: 82% ISO

Subject to order run minimums.

## Certifications

Using innovative manufacturing technology, Canfor Pulp Ltd. products are made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment.

Canfor Pulp Ltd. papers are certified for Forest Stewardship Council™ Chain of Custody and PEFC Chain of Custody.

Canfor Pulp Ltd. papers are manufactured in compliance with FDA 21 CFR 176.170 and 176.180, German recommendation XXXVI, CONEG heavy metals and EC directive 94/62/EC.

Certificates of compliance to all applicable regulatory requirements will be supplied upon request.

Effective: January 1, 2018

Canfor Pulp Ltd. paper is produced by Canfor Pulp Ltd. and marketed worldwide by Premium 1 Papers:



473 West Street, Kelowna, BC, Canada V1Y 4Z3  
 Tel: 250-870-5250 Fax: 250-870-5269 Toll Free: 1-866-611-5268  
 www.premium1papers.com  
 info@premium1papers.com

