



Bleached Beater Bag Kraft

End Uses:

A strong, bright, bleached paper, unsized for beater bag applications.

Fibre Source

British Columbia's northern forests produce some of the finest trees and fibre available for paper. The ideal climate encourages slow growth of white spruce, lodgepole pine and alpine fir. These trees produce cellulose fibres that are long, slender, flexible, and strong - providing an excellent furnish for kraft paper production. The readily collapsible thin cell walls of Canfor Pulp's fibres form ribbons with an exceptional surface area - promoting optimum fibre to fibre bonding for superior strength.

Typical Values – Metric (1924-3)

Basis Weight	g/m ²	80	Test Method
TEA	MD J/m ²	107	ISO 1924-3
	CD J/m ²	188	ISO 1924-3
TEA Index	MD J/g	1.3	ISO 1924-3
	CD J/g	2.3	ISO 1924-3
Tensile	MD kN/m	7.3	ISO 1924-3
	CD kN/m	4.5	ISO 1924-3
Stretch	MD %	2.3	ISO 1924-3
	CD %	6.3	ISO 1924-3
Porosity	s/100mL	19	ISO 5636-5
Tear	MD mN	923	ISO 1974
	CD mN	1012	ISO 1974

Paper
Laboratory
Conditions:
50% RH, 23°C

Subject to order run minimums.

Certifications

Using innovative manufacturing technology, Canfor Pulp Ltd. products are made under the ISO 9001 and 14001 management programs to ensure consistency in quality, service and protection to the environment.

Canfor Pulp Ltd. papers are certified for Forest Stewardship Council™ Chain of Custody and PEFC Chain of Custody.

Canfor Pulp Ltd. papers are manufactured in compliance with FDA 21 CFR 176.170 and 176.180, German recommendation XXXVI, CONEG heavy metals and EC directive 94/62/EC.

Certificates of compliance to all applicable regulatory requirements will be supplied upon request.

Effective: January 1, 2017

Canfor Pulp Ltd. paper is produced by Canfor Pulp Ltd. and marketed worldwide by Premium 1 Papers:



820A Guy Street, Kelowna, BC, Canada V1Y 7R5
Tel: 250-870-5250 Fax: 250-870-5269 Toll Free: 1-866-611-5268
www.premium1papers.com
info@premium1papers.com

